

Version number:REV.02

| | | | | | |
|---------|-----------|---------|--------|-----------|------------|
| OD | Weight | Wall Th | Grade | API Drift | Connection |
| 2.375in | 4.60lb/ft | 0.190in | CB150V | 1.901in | CBS3 |

| PIPE BODY PROPERTIES | |
|-----------------------------------|------------|
| Nominal OD | 2.375 in |
| Nominal ID | 1.995 in |
| Nominal Wall Thickness | 0.190 in |
| Minimum Wall Thickness | 87.5 % |
| Nominal Weight(API) | 4.60 lb/ft |
| Plain End Weight | 4.44 lb/ft |
| Drift | 1.901 in |
| Grade Type | API 5CT |
| Minimum Yield Strength | 150 ksi |
| Maximum Yield Strength | 180 ksi |
| Minimum Ultimate Tensile Strength | 160 ksi |
| Pipe Body Yield Strength | 196 klb |
| Internal Yield Strength | 21,000 psi |
| Collapse Pressure | 20,660 psi |

| CONNECTION PROPERTIES | |
|------------------------------|------------------------|
| Connection Type | Premium Thread&Coupled |
| Nominal Connection OD | 2.719 in |
| Nominal Connection ID | 1.957 in |
| Make-up Loss | 2.641 in |
| Coupling Length | 6.417 in |
| Tension Efficiency | 100% of Pipe Body |
| Compression Efficiency | 100% of Pipe Body |
| Internal Pressure Efficiency | 100% of Pipe Body |
| External Pressure Efficiency | 100% of Pipe Body |

| JOINT PERFORMANCES | |
|-------------------------------|-------------|
| Tensile Strength | 196 klb |
| Compression Strength | 196 klb |
| Internal Pressure Resistance | 21,000 psi |
| External Pressure Resistance | 20,660 psi |
| Maximum Bending | 30 °/100 ft |
| Maximum Load on Coupling Face | 141 klb |

| FIELD TORQUE VALUES | |
|----------------------|-------------|
| Min. Make-up torque | 1,430 ft-lb |
| Opti. Make-up torque | 1,580 ft-lb |
| Max. Make-up torque | 1,720 ft-lb |
| Min. Shoulder torque | 80 ft-lb |
| Max. Shoulder torque | 1,260 ft-lb |
| Min. Delta Turn | 0.010 turns |
| Max. Delta Turn | 0.120 turns |

Generated on 22/12/2024