CBJYJ2022-001(0385) REV.02 Effective Date: 2022.3.15

| OD | Weight | Wall Th | Grade | API Drift | Connection |
|---|---|---|---|---|---|
| 4.000in | 9.50lb/ft | 0.226in | N80Q | 3.423in | CBS3 |

| PIPE BODY PROPERTIES | |
|---|---|
| Nominal OD | 4.000 in |
| Nominal ID | 3.548 in |
| Nominal Wall Thickness | 0.226 in |
| Minimum Wall Thickness | 87.5 % |
| Nominal Weight(API) | 9.50 lb/ft |
| Plain End Weight | 9.12 lb/ft |
| Drift | 3.423 in |
| Grade Type | API 5CT |
| Minimum Yield Strength | 80 ksi |
| Maximum Yield Strength | 110 ksi |
| Minimum Ultimate Tensile Strength | 100 ksi |
| Pipe Body Yield Strength | 214 klb |
| Internal Yield Strength | 7,910 psi |
| Collapse Pressure | 6,590 psi |

| CONNECTION PROPERTIES | |
|---|---|
| Connection Type | Premium Thread&Coupled |
| Nominal Connection OD | 4.409 in |
| Nominal Connection ID | 3.500 in |
| Make-up Loss | 3.356 in |
| Coupling Length | 7.717 in |
| Tension Efficiency | 100% of Pipe Body |
| Compression Efficiency | 100% of Pipe Body |
| Internal Pressure Efficiency | 100% of Pipe Body |
| External Pressure Efficiency | 100% of Pipe Body |

| JOINT PERFORMANCES | |
|---|---|
| Tensile Strength | 214 klb |
| Compression Strength | 214 klb |
| Internal Pressure Resistance | 7,910 psi |
| External Pressure Resistance | 6,590 psi |
| Maximum Bending | 30 °/100 ft |
| Maximum Load on Coupling Face | 152 klb |

| FIELD TORQUE VALUES | |
|---|---|
| Friction Coefficient | 1 |
| Min. Make-up torque | 2,730 ft-lb |
| Opti. Make-up torque | 3,030 ft-lb |
| Max. Make-up torque | 3,320 ft-lb |
| Min. Shoulder torque | 150 ft-lb |
| Max. Shoulder torque | 2,420 ft-lb |
| Min. Delta Turn | 0.010 turns |
| Max. Delta Turn | 0.120 turns |

Generated on 22/11/2026