

Version number:REV.02

| | | | | | |
|---------|------------|---------|-------|-----------|------------|
| OD | Weight | Wall Th | Grade | API Drift | Connection |
| 4.000in | 10.90lb/ft | 0.262in | Q125 | 3.351in | CBS3 |

| PIPE BODY PROPERTIES | |
|-----------------------------------|-------------|
| Nominal OD | 4.000 in |
| Nominal ID | 3.476 in |
| Nominal Wall Thickness | 0.262 in |
| Minimum Wall Thickness | 87.5 % |
| Nominal Weight(API) | 10.90 lb/ft |
| Plain End Weight | 10.47 lb/ft |
| Drift | 3.351 in |
| Grade Type | API 5CT |
| Minimum Yield Strength | 125 ksi |
| Maximum Yield Strength | 150 ksi |
| Minimum Ultimate Tensile Strength | 135 ksi |
| Pipe Body Yield Strength | 385 klb |
| Internal Yield Strength | 14,330 psi |
| Collapse Pressure | 12,030 psi |

| CONNECTION PROPERTIES | |
|------------------------------|------------------------|
| Connection Type | Premium Thread&Coupled |
| Nominal Connection OD | 4.476 in |
| Nominal Connection ID | 3.437 in |
| Make-up Loss | 3.356 in |
| Coupling Length | 7.717 in |
| Tension Efficiency | 100% of Pipe Body |
| Compression Efficiency | 100% of Pipe Body |
| Internal Pressure Efficiency | 100% of Pipe Body |
| External Pressure Efficiency | 100% of Pipe Body |

| JOINT PERFORMANCES | |
|-------------------------------|-------------|
| Tensile Strength | 385 klb |
| Compression Strength | 385 klb |
| Internal Pressure Resistance | 14,330 psi |
| External Pressure Resistance | 12,030 psi |
| Maximum Bending | 30 °/100 ft |
| Maximum Load on Coupling Face | 297 klb |

| FIELD TORQUE VALUES | |
|----------------------|-------------|
| Min. Make-up torque | 4,060 ft-lb |
| Opti. Make-up torque | 4,500 ft-lb |
| Max. Make-up torque | 4,940 ft-lb |
| Min. Shoulder torque | 230 ft-lb |
| Max. Shoulder torque | 3,600 ft-lb |
| Min. Delta Turn | 0.010 turns |
| Max. Delta Turn | 0.120 turns |

Generated on 22/01/2025