

CBJY2022-001(0854) REV.02 Effective Date: 2022.3.15

| OD | Weight | Wall Th | Grade | API Drift | Connection |
|---------|------------|---------|-------|-----------|------------|
| 5.500in | 26.80lb/ft | 0.500in | C90 | 4.375in | CBS3 |

| PIPE BODY PROPERTIES | |
|-----------------------------------|-------------|
| Nominal OD | 5.500 in |
| Nominal ID | 4.500 in |
| Nominal Wall Thickness | 0.500 in |
| Minimum Wall Thickness | 87.5 % |
| Nominal Weight(API) | 26.80 lb/ft |
| Plain End Weight | 26.72 lb/ft |
| Drift | 4.375 in |
| Grade Type | API 5CT |
| Minimum Yield Strength | 90 ksi |
| Maximum Yield Strength | 105 ksi |
| Minimum Ultimate Tensile Strength | 100 ksi |
| Pipe Body Yield Strength | 707 klb |
| Internal Yield Strength | 14,320 psi |
| Collapse Pressure | 14,880 psi |

| CONNECTION PROPERTIES | |
|------------------------------|------------------------|
| Connection Type | Premium Thread&Coupled |
| Nominal Connection OD | 6.327 in |
| Nominal Connection ID | 4.648 in |
| Make-up Loss | 4.579 in |
| Coupling Length | 11.142 in |
| Tension Efficiency | 100% of Pipe Body |
| Compression Efficiency | 60% of Pipe Body |
| Internal Pressure Efficiency | 100% of Pipe Body |
| External Pressure Efficiency | 100% of Pipe Body |

| JOINT PERFORMANCES | |
|-------------------------------|-------------|
| Tensile Strength | 707 klb |
| Compression Strength | 424 klb |
| Internal Pressure Resistance | 14,320 psi |
| External Pressure Resistance | 14,880 psi |
| Maximum Bending | 30 °/100 ft |
| Maximum Load on Coupling Face | 564 klb |

| FIELD TORQUE VALUES | |
|----------------------|--------------|
| Friction Coefficient | 1 |
| Min. Make-up torque | 12,490 ft-lb |
| Opti. Make-up torque | 13,870 ft-lb |
| Max. Make-up torque | 15,260 ft-lb |
| Min. Shoulder torque | 690 ft-lb |
| Max. Shoulder torque | 11,100 ft-lb |
| Min. Delta Turn | 0.010 turns |
| Max. Delta Turn | 0.120 turns |

Generated on 07/07/2026