

CBJY2022-001(0568) REV.02 Effective Date: 2022.3.15

| OD | Weight | Wall Th | Grade | API Drift | Connection |
|---------|------------|---------|----------|-----------|------------|
| 4.500in | 15.10lb/ft | 0.337in | L80-13Cr | 3.701in | CBS3 |

| PIPE BODY PROPERTIES | |
|-----------------------------------|-------------|
| Nominal OD | 4.500 in |
| Nominal ID | 3.826 in |
| Nominal Wall Thickness | 0.337 in |
| Minimum Wall Thickness | 87.5 % |
| Nominal Weight(API) | 15.10 lb/ft |
| Plain End Weight | 15.00 lb/ft |
| Drift | 3.701 in |
| Grade Type | API 5CT |
| Minimum Yield Strength | 80 ksi |
| Maximum Yield Strength | 95 ksi |
| Minimum Ultimate Tensile Strength | 95 ksi |
| Pipe Body Yield Strength | 353 klb |
| Internal Yield Strength | 10,480 psi |
| Collapse Pressure | 11,090 psi |

| CONNECTION PROPERTIES | |
|------------------------------|------------------------|
| Connection Type | Premium Thread&Coupled |
| Nominal Connection OD | 5.063 in |
| Nominal Connection ID | 3.798 in |
| Make-up Loss | 3.419 in |
| Coupling Length | 7.953 in |
| Tension Efficiency | 100% of Pipe Body |
| Compression Efficiency | 100% of Pipe Body |
| Internal Pressure Efficiency | 100% of Pipe Body |
| External Pressure Efficiency | 100% of Pipe Body |

| JOINT PERFORMANCES | |
|-------------------------------|-------------|
| Tensile Strength | 353 klb |
| Compression Strength | 353 klb |
| Internal Pressure Resistance | 10,480 psi |
| External Pressure Resistance | 11,090 psi |
| Maximum Bending | 30 °/100 ft |
| Maximum Load on Coupling Face | 257 klb |

| FIELD TORQUE VALUES | |
|----------------------|-------------|
| Friction Coefficient | 1 |
| Min. Make-up torque | 5,610 ft-lb |
| Opti. Make-up torque | 6,200 ft-lb |
| Max. Make-up torque | 6,790 ft-lb |
| Min. Shoulder torque | 310 ft-lb |
| Max. Shoulder torque | 4,960 ft-lb |
| Min. Delta Turn | 0.010 turns |
| Max. Delta Turn | 0.120 turns |

Generated on 13/04/2026