

CBJY2022-001(3568) REV.02 Effective Date: 2022.3.15

| OD | Weight | Wall Th | Grade | API Drift | Connection |
|---------|------------|---------|------------|-----------|------------|
| 7.000in | 29.00lb/ft | 0.408in | CB125-13Cr | 6.059in | CBS3 |

| PIPE BODY PROPERTIES | |
|-----------------------------------|-------------|
| Nominal OD | 7.000 in |
| Nominal ID | 6.184 in |
| Nominal Wall Thickness | 0.408 in |
| Minimum Wall Thickness | 87.5 % |
| Nominal Weight(API) | 29.00 lb/ft |
| Plain End Weight | 28.75 lb/ft |
| Drift | 6.059 in |
| Grade Type | API 5CT |
| Minimum Yield Strength | 125 ksi |
| Maximum Yield Strength | 150 ksi |
| Minimum Ultimate Tensile Strength | 135 ksi |
| Pipe Body Yield Strength | 1,056 klb |
| Internal Yield Strength | 12,750 psi |
| Collapse Pressure | 9,110 psi |

| CONNECTION PROPERTIES | |
|------------------------------|------------------------|
| Connection Type | Premium Thread&Coupled |
| Nominal Connection OD | 7.717 in |
| Nominal Connection ID | 6.325 in |
| Make-up Loss | 4.973 in |
| Coupling Length | 11.929 in |
| Tension Efficiency | 100% of Pipe Body |
| Compression Efficiency | 60% of Pipe Body |
| Internal Pressure Efficiency | 100% of Pipe Body |
| External Pressure Efficiency | 100% of Pipe Body |

| JOINT PERFORMANCES | |
|-------------------------------|-------------|
| Tensile Strength | 1,056 klb |
| Compression Strength | 634 klb |
| Internal Pressure Resistance | 12,750 psi |
| External Pressure Resistance | 9,110 psi |
| Maximum Bending | 30 °/100 ft |
| Maximum Load on Coupling Face | 808 klb |

| FIELD TORQUE VALUES | |
|----------------------|--------------|
| Friction Coefficient | 1 |
| Min. Make-up torque | 11,230 ft-lb |
| Opti. Make-up torque | 12,470 ft-lb |
| Max. Make-up torque | 13,710 ft-lb |
| Min. Shoulder torque | 620 ft-lb |
| Max. Shoulder torque | 9,980 ft-lb |
| Min. Delta Turn | 0.010 turns |
| Max. Delta Turn | 0.120 turns |

Generated on 26/05/2026