

CBJY2022-001(3304) REV.02 Effective Date: 2022.3.15

OD	Weight	Wall Th	Grade	API Drift	Connection
4.500in	12.60lb/ft	0.271in	CB95S-13Cr	3.833in	CBS3

PIPE BODY PROPERTIES	
Nominal OD	4.500 in
Nominal ID	3.958 in
Nominal Wall Thickness	0.271 in
Minimum Wall Thickness	87.5 %
Nominal Weight(API)	12.60 lb/ft
Plain End Weight	12.25 lb/ft
Drift	3.833 in
Grade Type	API 5CT
Minimum Yield Strength	95 ksi
Maximum Yield Strength	110 ksi
Minimum Ultimate Tensile Strength	105 ksi
Pipe Body Yield Strength	342 klb
Internal Yield Strength	1,0000 psi
Collapse Pressure	8,410 psi

CONNECTION PROPERTIES	
Connection Type	Premium Thread&Coupled
Nominal Connection OD	4.968 in
Nominal Connection ID	3.913 in
Make-up Loss	3.419 in
Coupling Length	7.953 in
Tension Efficiency	100% of Pipe Body
Compression Efficiency	100% of Pipe Body
Internal Pressure Efficiency	100% of Pipe Body
External Pressure Efficiency	100% of Pipe Body

JOINT PERFORMANCES	
Tensile Strength	342 klb
Compression Strength	342 klb
Internal Pressure Resistance	1,0000 psi
External Pressure Resistance	8,410 psi
Maximum Bending	30 °/100 ft
Maximum Load on Coupling Face	235 klb

FIELD TORQUE VALUES	
Friction Coefficient	1
Min. Make-up torque	4,350 ft-lb
Opti. Make-up torque	4,870 ft-lb
Max. Make-up torque	5,380 ft-lb
Min. Shoulder torque	240 ft-lb
Max. Shoulder torque	3,890 ft-lb
Min. Delta Turn	0.010 turns
Max. Delta Turn	0.120 turns

Generated on 12/04/2026